

THE USER'S GUIDE TO CELCURE® MC-T3 PRESERVED WOOD

What is Celcure MC-T3 Preserved Wood ?

Celcure MC-T* preserved wood has been preserved by the correct application of Celcure MC-T3 wood preservative and then allowed to dry.

Properly treated Celcure MC-T3 preserved wood is protected against attack by wood decaying fungi and wood destroying insects.

Celcure MC-T3 preserved wood, treated to an appropriate specification, can be used for structural timber, sole plates, garden furniture, playground equipment, patios, decks, fencing, garden edging, and landscaping structures such as pergolas. Treated timbers must not be placed near or over water.

IMPORTANT INFORMATION

Wear gloves when working with wood. Only preserved wood that is visibly clean and free of surface residue should be used. Wear a dust mask and goggles when cutting or sanding wood.

Some preservative may migrate from the treated wood into soil/water or may dislodge from the treated wood surface upon contact with skin. Wash exposed skin areas thoroughly.

All sawdust and construction debris should be cleaned up and disposed of after construction. Wash work clothes separately from other household clothing before re-use.

If you desire to apply a paint, stain, clear water repellent or other finish to your preservative treated wood, we recommend following the manufacturer's instructions and label of the finishing product. Before you start, we recommend that you apply the finishing product to a small test area before finishing the entire project to ensure that it provides the intended result.

If the wood is to be used in an interior application and becomes wet during construction, it should be allowed to dry before being covered or enclosed.

Mould growth can and does occur on the surface of many products, including treated or untreated wood, during prolonged surface exposure to excessive moisture conditions. To remove mould from treated wood surfaces, wood should be allowed to dry. Typically, mild soap and water can be used to remove remaining surface mould.

Preserved wood should not be used where it may come into direct or indirect contact with drinking water, except for uses involving incidental contact such as fresh water docks and bridges.

Do not use preserved wood under circumstances where the preservative may become a component of food, animal feed or beehives.

Do not use preserved wood as mulch.

Do not burn preserved wood (see Disposal). All sawdust and construction debris should be cleaned up and disposed of after construction.

Effective Use of Preserved Wood

Cutting

Preserved wood should not be cut or otherwise reworked as this will expose unpreserved wood. If cutting cannot be avoided, then precautions should be taken to keep airborne dust levels below the Workplace Exposure Limits for wood dust. In particular, avoid inhalation of dust when using high speed cross-cut saws or mechanical sanders. Any surface exposed by drilling or cutting must be retreated with a cut end preservative. Failure to do this will reduce the effectiveness of the preservative. It is recommended that the re-preserved ends are not put in the ground or in direct contact with water. Rip sawing, thickening and planing are not permitted unless the timber is subsequently re-preserved to the original specification.

Metal Fastenings and Hardware

Celcure MC-T3 preserved wood has corrosion rates on metal products similar to untreated wood. Use fasteners and hardware that are in compliance with the manufacturer's recommendations and the building codes for their intended use.

Colour

Freshly treated Celcure MC-T3 preserved wood begins with a very light green colour and will turn to a honey tan colour after exposure to sunlight. As with most outdoor wood products, Celcure MC-T3 preserved wood will eventually fade to grey. Celcure MC-T3 preserved wood is lighter in colour compared to other copper based treated products, which benefits subsequent painting or staining. Celcure MC-T3 preserved wood is also available in various colours when produced in conjunction with the MicroShades* colour pigment system.

Installation

In decking, and as a general rule, nail boards bark side up (annual rings are upward) to reduce splitting; however the best face should be placed up when a defect of the wood is apparent. Fasten thin boards to thicker boards to maintain structural integrity. It is a good idea to drill pilot holes for your fixings when screwing near the edge or end of a board. This will minimise splitting. If the wood has become wet by exposure to rain, butt decking boards together during construction. As drying occurs, some shrinkage can be expected. If the wood is dry, space the boards to allow for expansion in wet weather. During the weathering of treated or untreated timber, extractives in the timber may run off and stain surrounding surfaces. Consideration should be given when intending to fix timber above surfaces where staining would be undesirable e.g. above light coloured render.

Gluing

Celcure MC-T3 preserved wood can be glued with most commonly used adhesives once dry. Always follow the adhesive manufacturer's recommendations.

Disposal

Celcure MC-T3 preserved wood that is no longer usable, such as off-cuts, broken boards, sawdust or preserved wood material taken out of service may be disposed of in landfills or burned in commercial or industrial incinerators or boilers in accordance with national and local regulations. For up to date information please contact the Technical Services Department.

Biocidal Product Regulation (EU 528/2012) Article 58 Information

Celcure MC-T3 preserved wood is a "treated article" which incorporates biocidal products.

Wood correctly preserved with Celcure MC-T3 is protected against wood destroying insects and wood rotting fungi.

Contains: Basic copper carbonate (Copper (II) carbonate – Copper (II) hydroxide (1:1)), Tebuconazole.

ADDITIONAL INFORMATION

Celcure MC-T3 preserved wood products are produced by independently owned and operated wood preserving facilities.

Koppers Performance Chemicals provides a range of products and technologies for the treatment, protection and enhancement of timber. Information and advice is available on all aspects of our products from the Technical Services Department.

For more information visit www.kopperspc.eu

Or contact: kpc@koppers.eu
Telephone: +44 (0) 1628 486644
Emergency: +44 (0) 1628 890907

Celcure is a registered trademark of Protim Solignum Ltd, trading as Koppers Performance Chemicals

Protim Solignum Limited's products are sold subject to its standard Terms and Conditions of Sale, copies of which may be obtained on request. Whilst Protim Solignum endeavours to ensure that any advice, recommendation, specification or information it may give is accurate and correct, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products, whether or not in accordance with any advice, specification, recommendation or information given by it save as specifically provided by its Terms and Conditions of Sale.

Protim Solignum Ltd

Fieldhouse Lane, Marlow, Bucks SL7 1LS, UK. Tel: +44 (0)1628 486644. Fax: +44 (0)1628 476757
Registered in England - 3037845 | Registered Office: Fieldhouse Lane, Marlow, Bucks SL7 1LS, UK.
Copyright © Koppers Performance Chemicals – IS/100 November 2017



FM01724



FM36409